



Possible use - Standofleet 2K Thinner

Temperature	Small objects (individual door, fender, ...)	Medium-sized objects (Transporters, driver's cabs, side / board panel, ...)	Larger areas of more than one overlapping area (constructional parts, walls > 1,5 m height, ...)
10 - 20°C	2K Thinner Fast	2K Thinner Fast 2K Thinner	2K Thinner
20 - 30°C	2K Thinner Fast 2K Thinner	2K Thinner	2K Thinner Slow
30 - 40°C	2K Thinner	2K Thinner Slow	2K Thinner Extra Slow

Air flow conditions, application systems, humidity, etc. have a further influence.

Details:

Standofleet 2K Thinner Fast

- Short flash off time
- Small, individual objects, Spot Repair
- Stripes & lettering
- Spray temperature 18-20°C

Standofleet 2K Thinner

- Standard 2K Thinner
- Medium-sized objects
- Spray temperature 20-25°C

Standofleet 2K Thinner Slow

- Large objects
- Spray temperature 25-30°C

Standofleet 2K Thinner Extra Slow

- Long flash off time
- Large objects
- Spray temperature more than 30°C